

Typical pulp characteristics ASPEN 350/84 B

100% Aspen TCF BCTMP, Flash Dried

	Freeness	Bright ness	Bulk	Bulk	Opacity	Tensile Index	Light scattering
	CSF ml	% ISO	cm ³ /g	cm ³ /g	% ISO	Nm/g	m ² /kg
	ISO 5267	ISO 2470	ISO 534	Tappi T411	ISO 2471	ISO 1924-2	ISO 9416
ASPEN 350/84 B	350 +/-40	83,5	2,0	2,35	85	25	43

SALES OVER:

heinzel[®]sales

WILFRIED HEINZEL AG

www.heinzelsales.com