

Typical pulp characteristics ASPEN 450/80 HB

100% Aspen TCF BCTMP, Flash Dried

	Freeness	Bright ness	Bulk	Bulk	Opacity	Tensile Index	Light scattering
	CSF ml	% ISO	cm ³ /g	cm ³ /g	% ISO	Nm/g	m ² /kg
	ISO 5267	ISO 2470	ISO 534	Tappi T411	ISO 2471	ISO 1924-2	ISO 9416
ASPEN 450/80 HB	450 +/-50	80,5	2,3	2,8	85	19	43

SALES OVER:

heinzelsales[®]

WILFRIED HEINZEL AG

www.heinzelsales.com