

ASPEN 350/84 MB

Pulp characteristics (indicative) TCF, Flash Dried									
Freeness	Brightness	Bulk	Bulk	Tensile Index	Opacity	Light Scattering	Shives Sommerville	Air resistance Gurley	pH
CSF ml	% ISO	cm ³ /g	cm ³ /g	Nm/g	% ISO	m ² /kg	% 0,15 slot	S	
ISO 5267	ISO 2470 ISO 3688	ISO 534 ISO 5269-2	ISO 534 / 5269-1 TAPPI T411	ISO 1924-2 ISO 5269-2	ISO 2471 ISO 5269-2	ISO 9416 ISO 5269-2	TAPPI T275	ISO 5636-5 ISO 5270	TAPPI T252
350 +/- 50	83,7 min 83	1,80	2,30	30	83	40	0,02	9	7-8



Certificates	
Quality system	9001:2008
Environmental management system	14001:2004
Chain of custody / Controlled wood	FSC COC/CW
Conformity with food contact materials	ISEGA 2792 U 09

ASPEN 350/84 MB



Bale size (l x w x h in cm): 90 x 63 x 49	
Gross weight	ca. 237 kg (ca. 230 ADkg)
Bale wire	1-2 (galvanized) x Ø 2,3 mm
Wrapping	Bleached Kraft Paper
Markings	Brand name, bale number

Unit size (l x w x h in cm): 90 x 130 x 199	
Gross weight	ca. 1896 kg (ca. 1840 ADkg)
Unit wire	6 (galvanized wires) x Ø 3,0 mm
Unit	8 bales



HEINZEL GROUP®



28.07.2015

www.estoniancell.ee
www.heinzelsales.com