

## ASPEN 350/85 HT



Pulp characteristics (indicative) TCF, Flash Dried									
Freeness	Brightness	Bulk	Bulk	Tensile Index	Opacity	Light Scattering	Shives Sommerville	Air resistance Gurley	pH
CSF ml	% ISO	cm <sup>3</sup> /g	cm <sup>3</sup> /g	Nm/g	% ISO	m <sup>2</sup> /kg	% 0,15 slot	S	
ISO 5267	ISO 2470 ISO 3688	ISO 534 ISO 5269-2	ISO 534 / 5269-1 TAPPI T411	ISO 1924-2 ISO 5269-2	ISO 2471 ISO 5269-2	ISO 9416 ISO 5269-2	TAPPI T275	ISO 5636-5 ISO 5270	TAPPI T252
350 +/- 50	84,5	1,65	2,15	39	81	35	0,02	15	7-8

Main uses
Printing and writing papers
Coated and uncoated papers
Speciality papers

Certificates	
Quality system	9001:2008
Environmental management system	14001:2004
Chain of custody / Controlled wood	FSC COC/CW
Conformity with food contact materials	ISEGA 2792 U 09

## ASPEN 350/85 HT



Bale size (l x w x h in cm): 90 x 63 x 49	
<b>Gross weight</b>	ca. 237 kg (ca. 229 ADkg)
<b>Bale wire</b>	1 (galvanized) x Ø 2,3 mm
<b>Wrapping</b>	Bleached Kraft Paper
<b>Markings</b>	Brand name, bale number

Unit size (l x w x h in cm): 90 x 130 x 199	
<b>Gross weight</b>	ca. 1896 kg (ca. 1832 ADkg)
<b>Unit wire</b>	6 (galvanized wires) x Ø 3,0 mm
<b>Unit</b>	8 bales

